




Professional Gypsum Fairway

Analysis:

| | |
|--|-------|
| Calcium (Ca) | 21% |
| Sulfur (Su) | 14% |
| Calcium Sulfate (CaSo4) | 68% |
| Calcium Sulfate Dihydrate (CaSo4-2H20) | 86.5% |
| Water Soluble Binder-lignosulfonate | 2.0% |
| Moisture (Maximum) | 4.0% |
| Derived from mined Calcium Sulfate | |

Aesthetics

Gypsum Fairway



| | |
|---------------------------|--|
| <u>Size:</u> | SGN: Range of 260 to 270 Diameter: 3.1 to 4.1 millimeters |
| <u>Shape:</u> | Small Pearl |
| <u>Density:</u> | 72 to 74 lbs/cubic ft |
| <u>Durability:</u> | 3 to 5 Crush test (Foot pounds of Force) |
| <u>Fines:</u> | 5% max |
| <u>Odor:</u> | Slight Mineral Order |
| <u>Color:</u> | Light Brownish Grey Cast with a tinge of Purple |

